APPLICATION
FOR
UNITED STATES
LETTERS PATENT

Applicants: Shuya Ogi, Takashi Fukuzawa, Koichiro
Iki, Masahide Wakisaka and Kiyotaka Sasaki
For: ROD LENS ARRAY AND A PROCESS FOR
PRODUCING THE SAME
Docket No.: N36-135856M/TH

ROD LENS ARRAY AND A PROCESS

FOR PRODUCING THE SAME

BACKGROUND OF THE INVENTION

This invention relates to a process for producing a rod
lens array in which a multiple of gradient index rod lenses are
precision arranged parallel to each other at given spacings and

5   fixed between two side plates (frames) as they are buried in
a resin. The rod lens array is typically useful as an optical
component for an image writing system in an electrophoto-graphic
printer.

The rod lens array is an optical component that has a multiple

10 of tiny gradient index rod lenses arranged in alignment so that
they combine together to form a single continuous erected
unit-magnification image. The rod lens array has a short optical
pathlength and needs no inverting mirror; because of the
size-reducing feature, the rod lens array is commonly used as

15 an optical component not only for an image reading system in
an image scanner, a copier, etc. but also for an image writing
system that forms a latent image on a photoreceptor in accordance
with   supplied   image   signals.   Recent   models   of
electrophotographic printer have been improved to achieve high

20 image resolution comparable to that offered by silver halide

- 1 -

photography. This has accordingly increased the requirement for higher precision in latent image and, hence, for better quality of image writing optical components in terms of the precision of the position in which image is formed.

5   A common process for the production of the rod lens array includes an assembly step in which a multiple of lens preformers are arranged in contact with each other and fixed between an upper and a lower side plate (frame plate) to form a block, an impregnation and curing step in which a resin is impregnated

10   between the individual lens preformers in the block, and a cutting step in which the block is cut to a specified lens length. The side plates are usually fiber glass-reinforced plastic laminated plates (FRP plates).

In the assembly step, two methods are commonly used. In

15   one method, a plurality of gradient index rod lenses are aligned on a flat frame such that their outer peripheral surfaces contact each other and they are altogether fixed to maintain the aligned state (this method is hereunder referred to as the "diameter referenced method"). The other method uses an aligning tool

20   having a plurality of V-shaped grooves cut side by side in the surface of a platen on specified pitches, and gradient index rod lenses placed in the respective V-shaped grooves are fixed altogether to maintain their aligned state (this method is hereunder referred to as the "mechanically referenced method";

25   see JP 9-90105 A).

- 2 -

The surface of an FRP plate has fine periodical asperities due to the texture of the woven glass fabric used in its production and hence the individual lens preformers are likely to be offset positionally during the assembly and impregnation steps.

5   Positional offset also occurs due to the warpage of lens preformers and their surface roughness. In addition, both the diameter referenced method and the mechanically referenced method have their own problems.

Consider, for example, an image writing system of the type

10   shown in Fig. 11; a light emitting portion (LED device) 10 blinks in accordance with image signals and a rod lens 12 forms a latent image on an imaging surface (photoreceptor drum) 14. Any deviation from the desired alignment of rod lenses 12 results in a great variation in the potential at which the latent image is formed

15   on the photoreceptor drum. On account of this variation in the imaging position that results from misalignment of the rod lenses, the image resolution that can be achieved by the image writing optical system is limited.

To make an acceptable rod lens array, gradient index rod

20   lenses must be aligned such that adjacent lenses have a constant axial spacing (or "alignment pitch") and that there be neither inclination in the plane of alignment (which is hereunder referred to as "horizontal inclination") nor inclination in a direction normal to the plane of alignment (which is hereunder referred

25   to as "height inclination"). The height inclination can be

- 3 -

suppressed in the diameter referenced method. On the other hand, due to contact between gradient index rod lenses, a horizontally inclined lens affects an adjacent lens and the lenses taken as a whole may occasionally be inclined horizontally to suffer "axial

5   displacement". In the case of a printer or facsimile, this causes an image to be formed in a position far distant from where it should be.

     The mechanically referenced method can provide higher precision in lens alignment. On the other hand, individual

10   gradient index rod lenses sometimes fail to be placed uniformly within V-shaped grooves in the platen, causing one lens to be inclined with respect to another. Since it is unavoidable that lens preformers vary in diameter, the setting of the pitch between grooves in the platen must not be smaller than a maximum value

15   for the variation in the diameter of lens preformers. As a result, very small gaps occur between arranged lens preformers and positional offset may occur during the mounting of side plates.

     In the "partial" burial step where one side plate is mounted, the grooved platen adequately protects against positional offset

20   but in the "complete" burial step where the grooved platen is removed and the other side plate is mounted, the precision in the alignment of lens preformers may drop since there is nothing that controls the positional offset. In a printer or facsimile, this is a cause of failures such as an overlap of pixels.

25   Next, we describe the positional offset of rod lenses and

- 4 -

their departure from the desired alignment on account of their

surface roughness. The rod lenses to be used in the rod lens

array are mainly produced by ion-exchange. As shown graphically

in Fig. 17, a beam of incident light which falls on an end face

5   of a rod lens 12 at an angle smaller than its angular aperture

θ_0 is an effective ray 21. On the other hand, a beam of light

incident at an angle greater than θ_0 undergoes regular reflection

at the internal specular surface .of the rod lens 12 which is

manufactured by drawing. The reflected beam is so-called "stray"

10   light 22 which takes no part in image. formation and therefore

lowers the contrast of the rod lens 12. Furthermore, the rod

lens array is constructed by a multiple of rod lenses ·12 and

the stray light 22 occurring in individual rod lenses 12 will

reduce the overall contrast of the rod lens array.

15   In known rod lens arrays, a multiple of rod lenses arranged

in one or two rows are fixed between two frame plates and a black

silicone resin is filled between lenses and between each frame

plate and lenses.

Fig. 18 shows a conventional method of removing stray light

20   22 by allowing it to scatter. To this end, the peripheral surface

of the rod lens 12 is removed to some extent by a surface treatment

and tiny asperities 23 are formed around it (see, for example,

JP 58-38901 A). The stray light 22 incident on the surface of

the area where asperities 23 are formed is scattered as indicated

by 25.   In addition, the black silicone resin 24 covering the peripheral surface of the rod lens 12 absorbs the scattered light 25, eventually suppressing the stray light 22.

5   In fact, however, the peripheral surface of the conventional rod lens has a profile as shown in Fig. 19 and suffers the following disadvantages.   Fig. 19 shows the roughness, or the degree of unevenness, of the peripheral surface of a rectilinear area in the longitudinal direction of the conventional rod lens.

        The first problem arises from the fact that the amount of
10   removal from the peripheral lens surface varies from one lens to another and so does the lens diameter.   If the rod lenses are arranged with reference to the frame plates, there occurs a departure from the desired lens arrangement due to the variation in lens diameter and the optical axis of one rod lens is inclined
15   with respect to the optical axis of another.

        Secondly, due to the lens-to-lens difference in the roughness of the peripheral lens surface, there occurs a variation in the effective aperture of the lens that contributes to satisfactory imaging.   This causes a variation in the resolving power of the
20   rod lens array in a longitudinal direction.   With decreasing surface asperities, the lens surface has an increased degree of specularity and becomes more susceptible to the effect of stray light; it is therefore considered necessary that the peripheral surface of each rod lens have a center-line-average
25   roughness of at least 0.5 μm.

SUMMARY OF THE INVENTION

The present invention has been accomplished under these circumstances and has as an object providing a high-performance rod lens array that can be produced by the mechanically referenced method and which still features good axial alignment without suffering the inconsistency in the pitch on which gradient index rod lenses are arranged and two types of inclination, height and horizontal.

Another object of the invention is to provide a process for producing a rod lens array which not only prevents lens preformers from being positionally offset while they are arranged but which can also constrain their movement during installation of side plates, thereby suppressing the variation in the arrangement of lens preformers (their positional offset).

Another object of the invention is to provide a process for producing a rod lens array which can suitably be used as a component in an image writing optical system to insure higher precision in the imaging position.

Yet another object of the invention is to provide a process for producing a rod lens array using side plates furnished with a means for constraining the movement of lens preformers which can be easily formed in high dimensional precision and at low cost, allowing for the use of lens preformers of smaller diameter.

Further another object of the invention is to provide rod lenses that can be arranged with a small enough departure from

- 7 -

the desired alignment to produce a rod lens array that will experience minimum variations in resolving power in a longitudinal direction.

The present inventors studied how the spacing between adjacent gradient index rod lenses to be used in producing a rod lens array by the mechanically referenced method would affect their alignment pitch of, as well as their height and horizontal inclinations. As a result, they found that by setting the spacing to lie within a specified range, the variation in the alignment pitch of rod lenses, the variation in their height inclination (standard deviation, hereunder referred to as "height variation") and the variation in their horizontal inclination (standard deviation, hereunder referred to as "horizontal variation") could be reduced to their minimum levels. The present invention has been accomplished on the basis of this finding.

In order to attain the stated objects, the present invention provides the following two processes for production.

(1) A process for producing a rod lens array comprising the steps of providing an aligning tool having a plurality of grooves formed side by side, placing gradient index rod lenses in alignment within the grooves at an average spacing of 1 μm – 5 μm, fixing the gradient index rod lenses to form an integral unit as they maintain the aligned state, and thereafter polishing the end faces of each rod lens.

(2) A process for producing a rod lens array comprising the steps

- 8 -

of providing an aligning tool having a plurality of grooves formed side by side, placing gradient index rod lenses in alignment within the grooves at an average spacing of 1 μm - 5 μm, then fixing the gradient index rod lenses as they maintain the aligned

5   state, thereafter removing the aligning tool, then cutting each rod lens to a specified lens length, and thereafter polishing the end faces of each rod lens.

To attain similar objects, the present invention provides a rod lens array that is produced by the process described above

10   in (1) or (2) and which has the gradient index rod lenses aligned at an average spacing of 1 μm - 5 μm.

The present invention provides a process for producing a single-row rod lens array comprising:

a lens preformer arranging step in which a grooved platen

15   having a multiple of shallow grooves to receive gradient index rod lens preformers formed parallel to each other at equal spacings is supplied with a multiple of lens preformers such that they are placed in alignment within said shallow grooves;

a partial burial step in which an impregnating resin sheet

20   and a side plate are placed in a face-to-face relationship with the group of arranged lens preformers, then heat is applied to render said resin sheet viscous and pressure is also applied so that the individual lens preformers are bonded to the side plate as they are partially buried in the resin and, thereafter,

the bonded lens preformers are detached from said platen; and

a complete burial step in which an impregnating resin sheet and a side plate are placed in a face-to-face relationship with the partially buried lens preformers in array form, then heat

5   is applied to render said resin sheet viscous and pressure is also applied so that the individual lens preformers are bonded to the side plate as they are buried completely in the resin;

characterized in that a side plate with a striped pattern of multiple ridges that extend along the lens preformers are

10   arranged on the same pitch as the lens preformers on the surface of a side plate substrate which is to bear the lens preformers is used as the side plate in the partial burial step or in both partial and complete burial steps and the lens preformers are bonded to said side plate such that each of them is located between

15   adjacent ridges.

The present invention also provides a process for producing a two-row rod lens array comprising:.

a lens preformer arranging step in which a grooved platen having a multiple of shallow grooves to receive gradient index

20   rod lens preformers formed parallel to each other at equal spacings is supplied with a multiple of lens preformers such that they are placed in alignment within said shallow grooves;

a partial burial step in which an impregnating resin sheet and a side plate are placed in a face-to-face relationship with

25   the group of arranged lens preformers, then heat is applied

- 10 -

to render said resin sheet viscous and pressure is also applied

so that the individual lens preformers are bonded to the side

plate as they are partially buried in the resin and, thereafter,

the bonded lens preformers are detached from said platen; and

5   a complete burial step in which an impregnating resin sheet

is placed between two arrays of the partially buried lens preformers

such that the lens preformers in one array are in a face-to-face

relationship with those in the other array, then heat is applied

to render said resin sheet viscous and pressure is also applied

10   so that the individual lens preformers are bonded to the side

plate as they are buried completely in the resin;

        characterized in that a side plate with a striped pattern

of multiple ridges that extend along the lens preformers are

arranged on the same pitch as the lens preformers on the surface

15   of a side plate substrate which is to bear the lens preformers

is used as the side plate in the partial burial step and the

lens preformers are bonded to said side plate such that each

of them is located between adjacent ridges.

        In order to reduce the positional offset that may occur

20   in imaging by the rod lens array, the variation in the arrangement

of lens preformers has to be reduced. The variation in lens

arrangement occurs not only when the lens preformers are arranged;

it also occurs if lens preformers move during installation of

side plates. In the present invention, the movement of lens

25   preformers is constrained by the ridges which are formed on the

- 11 -

side plates per se. Since these ridges are provided on the side
plate substrate which is part of the final product per se, they
have to be formed at low enough cost and, in addition, must satisfy
high dimensional precision requirements so that lens preformers
5   of smaller diameter (D ≤ 1 mm) can be used. As a prior art technique,
JP 7-46383 A has proposed that groove shapes be formed in the
side plates of a lens array. To form groove shapes, grooves
may be transferred to the side plates by pressing or they may
be cut by mechanical working. However, realizing the depth and
10   pitch of grooves that have sufficient precision to permit the
use of finer rod lenses requires sophisticated facilities and
high cost and, hence, is not practically feasible. In the present
invention, a multiple of ridges rather than grooves are formed
in high precision. Ridges are preferably formed by screen printing
15   or photolithography. By either method, ridges of a rectangular
cross section can be formed in precise alignment.

In the case of screen printing, a coating is desirably applied
to the entire surface of one side of a side plate substrate to
form an undercoat and a multiple of ridges to assist in arrangement
20   of lens preformers are formed on the undercoat. The undercoat
may be formed by applying one or two layers of a coat having
a thickness of 5 - 15 μm; the ridges may have a thickness of
10 - 30 μm that is relatively easy to control in precision; the
pitch of the ridges may be set at a value near the maximum variation

- 12 -

in the diameter of lens preformers that is anticipated in the manufacturing process.

The side plate substrate may be a fiber glass-reinforced plastic laminated plate (FRP plate) or a glass plate. The undercoat
5   is effective in reducing the tiny surface asperities that have been caused by the texture of the woven glass fabric. In the case of a glass plate, it is rendered light-opaque by mixing with a black pigment or the like so as to impart the ability to prevent leaky light (stray light). To insure adequate bonding
10 strength at the interface with the resin to be impregnated between lens preformers, an epoxy resin based coating is desirably used to form the undercoat and ridges.

In the case of photolithography, a resist is applied to the entire surface of the side plate substrate which is then
15 exposed to light through a mask and the areas that have become soluble are etched away to form a multiple of ridges in a desired pattern. Preferably, the conditions for resist application and etching are controlled such that ridges 10 - 30 μm thick are formed on the underlying resist blanket having a thickness of
20 5 - 15 μm.

The present invention provides a rod lens having a center-line-average roughness of 0.5 μm - 2.0 μm on the peripheral surface.

It has been verified that if the peripheral surface of the

- 13 -

rod lens has a center-line-average roughness of 0.5 μm - 2.0 μm, the effect of stray light can be eliminated to suppress the variation in resolving power.

5   The present invention also provides a rod lens array in which the constituent rod lenses are such that representative values for the center-line-average roughness on their peripheral surfaces are between 0.01 μm and 0.2 μm as averaged for the whole lens array.

     This design has also been verified to be effective in
10   eliminating the effect of stray light to suppress the variation in resolving power.

     The present invention also provides a rod lens array in which the constituent rod lenses are such that representative values for the center-line-average roughness on their peripheral
15   surfaces are between 0.01 μm and 0.2 μm as expressed by standard deviation for the whole lens array.

     With this design, variation is less likely to occur in the effective lens aperture which contributes to image formation.

     The present invention also provides a rod lens array in
20   which the constituent rod lenses are such that representative values for their diameters are between 0.01 μm and 2.5 μm as expressed by standard deviation for the whole lens array.

     With this design, departures from the desired lens arrangement are less likely to occur from the variation in rod lens diameter.

- 14 -

The representative values for the center-line-average roughness may each be a value on a straight line that extends on the peripheral surface of the lens parallel to its axis. Alternatively, they may each be the average of values on different

5   straight lines that extend on the peripheral surface of the lens along its axis.

Each of the rod lens arrays described above has preferably a resin portion that is integral with the constituent rod lenses such that it fills the gap between adjacent rod lenses and surrounds

10   all rod lenses.

In this design, the rod lenses are surrounded by the resin and stray light can be absorbed most effectively if the resin is a good light absorber such as a black resin.

Preferably, a frame plate is fixed to at least one of the

15   two outer surfaces of said resin portion which are lateral to the thickness of the array.

With this design, a plurality of rod lenses can be easily arrayed with the frame plate used as a guide. As a result, a highly precise rod lens array can be realized.

20   The present disclosure relates to the subject matter contained in Japanese patent application Nos. 2000-298424 (filed on September 29, 2000), 2000-343212 (filed on November 10, 2000) and 2001-40110 (filed on February 26, 2001), which are expressly incorporated herein by reference in their entireties.

25   BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1A is a plan view illustrating how a plurality of gradient index rod lenses are arrayed;

Fib. 1B is a sectional view of the arrayed rod lenses;

Fig. 2 is a graph showing experimental data for the

5 relationship the spacing of gradient index rod lenses has with the variation in their alignment pitch and the horizontal variation;

Fig. 3 is a graph showing experimental data for the relationship between the spacing of gradient index rod lenses

10 and their height variation;

Fig. 4 is a graph showing experimental data for the relationship between the spacing of gradient index rod lenses and the variation in their alignment pitch;

Fig. 5A is a perspective view of an exemplary side plate

15 to be used in the process of the invention;

Fig. 5B is a section of Fig. 5A;

Figs. 6A – 6C show steps in a process for preparing an array of partially buried lens preformers;

Fig. 7 shows a step in a process for preparing a single-row

20 array of lens preformers;

Fig. 8 shows an exemplary single-row array of lens preformers;

Fig. 9 shows a step in a process for preparing a two-row array of lens preformers;

Fig. 10 shows an exemplary two-row array of lens preformers;

25 Fig. 11 shows how a departure from the desired lens arrangement

in an image writing optical system affects the potential at which a latent image is formed;

Fig. 12 is a perspective view of a rod lens array in one embodiment of the invention;

5   Fig. 13 is a graph showing asperities on the peripheral surface of a rod lens in the same array;

Fig. 14 is a graph showing the result of MTF measurement on rod lens array B of Example 1;

Fig. 15 is a graph showing the result of MTF measurement
10   on rod lens array C of Example 1;

Fig. 16 is a graph showing the result of MTF measurement on rod lens array E of Example 2;

Fig. 17 shows in section how stray light occurs in a rod lens;

15   Fig. 18 shows in section how stray light can be suppressed in a rod lens;

Fig. 19 is a graph showing asperities on the peripheral surface of a comparative rod lens;

Fig. 20 is a graph showing the result of MTF measurement
20   on comparative rod lens array A;

Fig. 21 is a graph showing the result of MTF measurement on comparative rod lens array D; and

Fig. 22 shows a roughness curve f(X) in relation to the sampling length L and the center line.

25   DESCRIPTION OF THE PREFERRED EMBODIMENT

- 17 -

The present invention is described below in detail with
reference to accompanying drawings. Fig. 1A is a top view showing
how a plurality of gradient index rod lenses 101 are placed within
V-grooves 103 in an aligning platen 102. Fig. 1B is a side view
5   of the gradient index rod lenses as seen from an end. Suppose
the gradient index rod lenses 101 shown in Fig. 1A are spaced
on pitches a1, a2, a3, ... at one end and on pitches b1, b2,
b3, ... at the other end, as measured between longitudinal axes
A. Then, the horizontal inclinations of the respective rod lenses
10   101 are expressed by (b1 - a1), (b2 - a2), (b3 - a3), ... If
adjacent rod lenses 101 are parallel to each other, the lens-to-lens
distance L is expressed by the difference between the lens diameter
D and the pitch of V-grooves. Therefore, the lens-to-lens distance
L can be adjusted to a desired value by controlling the lens
15   diameter D and the pitch of V-grooves.

To confirm this finding, the present inventors prepared
an aligning platen 102 having about 400 V-grooves cut at spacings
of 570 μm. As gradient index rod lenses 101, the inventors used
four types that were 100 mm long and which were 570 μm, 568 μm,
20   566 μm and 564 μm in diameter D. The rod lenses of each type
were placed within the V-grooves in the platen 102 and transferred
onto a frame having an adhesive coat. The resulting variation
in alignment pitch, as well as horizontal and height variations
were measured for each type of rod lenses. The frame (side plate)

- 18 -

was formed of either glass or FRP (fiber glass-reinforced plastic).
The four types of rod lenses had the following relationships
between D and L (both in micrometers).

Diameter D	Lens-to-lens Distance L
570	0
568	2
566	4
564	6

5

10   The measurements were conducted by the stylus tracer method.
As Fig. 1A shows, the probe was traversed across the peripheral
surface of each rod lens 101 over a sampling length of 4 mm parallel
to lens length. A circle having a diameter equivalent to D was
fitted to each of the measured surface profiles and the position
of its center was determined to calculate the pitch between lenses

15   and the height of each lens. On the basis of the measurements
in two positions, the horizontal and height inclinations were
calculated to determine the variation (standard deviation) for
the entire part of a particular lens array. Table 1 shows three
kinds of variation, the variation in alignment pitch, the
horizontal variation and the height variation, for each tested

20   value of the lens-to-lens distance L of rod lenses 101. The
variation in alignment pitch and the horizontal variation are
plotted in Fig. 2, and the height variation in Fig. 3.
Table 1

		Lens-to-lens distance L (μm)			
		6	4	2	0
Glass Frame	Alignment pitch	1.09	0.93	0.72	3.99
	Horizontal variation	0.43	0.31	0.29	0.43
	Height variation	0.45	0.54	0.60	1.39
FRP Frame	Alignment pitch	1.08	0.99	0.73	3.66
	Horizontal variation	0.59	0.67	0.46	0.35
	Height variation	1.05	0.83	0.74	2.64

As Table 1 shows, the variation in alignment pitch could be suppressed by adjusting the lens-to-lens distance L to lie within the range of 2 μm - 5 μm; the horizontal variation could be suppressed by adjusting L to lie within the range of 1 μm - 5 μm; the height variation could be suppressed by adjusting L to lie within the range of 2 μm - 5 μm. One may therefore conclude that for balanced suppression of the variation in alignment pitch, horizontal variation and height variation, it is generally effective to specify the lens-to-lens distance L

- 20 -

of gradient index rod lenses 101 to lie within the range of 1 μm - 5 μm, preferably within the range of 2 μm - 5 μm. This conclusion holds irrespective of whether the frame is formed of glass or FRP.

5   A similar experiment was performed on other values for the diameter (D) of gradient index rod lenses 101. The platen 102 was accordingly changed to one having V-grooves formed on a pitch of 305 μm. Evaluation was made for the case of using a glass frame. The rod lenses had the following relationships between

10   D and L (both in micrometers).

Diameter D	Lens-to-lens Distance L
305	0
303	2
301	4
298	7
296	9

      Similarly, the variation in lens pitch was determined by the stylus tracer method. The result is shown in Table 2 and Fig. 4. The data also shows that the variation in alignment

20   pitch could be suppressed by adjusting the lens-to-lens distance L of rod lenses 101 to lie within the range of 2 μm - 5 μm.

Table 2

Lens-to-lens distance (μm)	2	4	7	9

- 21 -

Deviation   0.85   1.22   1.48   1.33

     The foregoing experiments have shown that in order to produce a rod lens array by aligning a plurality of gradient index rod

5   lenses 101 on the V-grooved platen 102, the lens diameter D and the pitch of V-grooves are desirably set at such values that the lens-to-lens distance L of adjacent rod lenses 101 is in the range of 1 µm – 5 µm, preferably in the range of 2 µm – 5 µm. In most cases of the actual manufacturing process, the lens

10 diameter D is preliminarily set in accordance with the specifications of the rod lens array to be produced, so it is common practice to use a platen having V-grooves that have been so designed that the difference between D and the pitch of V-grooves is between 1 µm and 5 µm, preferably between 2 µm and 5 µm.

15 Note that the grooves to be formed in the platen need not be V-shaped but may be U-shaped or semicircular.

     Hence, the process of the present invention for producing a rod lens array is also implemented by using a V-grooved platen 102 on which the pitch of V grooves has been set in accordance

20 with the diameter D of the gradient index rod lenses 101. Described below is a preferred embodiment of the present invention as it relates to a process for producing a rod lens array.

     To begin with, gradient index rod lenses 101 having a specified lens length are placed within the V-grooves in the platen 102

- 22 -

which has been designed to have a specified pitch of V grooves
that conform to the lens diameter D. Then, an adhesive is filled
in the gap between rod lenses 101 and subsequently cured so that
adjacent rod lenses will be bound together. Instead of filling
5   the adhesive, an adhesive sheet may be placed over all rod lenses
101 and subsequently pressed down until the rod lenses 101 are
buried to a specified depth in the adhesive sheet. Thereafter,
both end faces of each rod lens 101 are polished and the grooved
platen 102 is removed to leave a rod lens array behind which
10   is an integral assembly of gradient index rod lenses 101 that
are aligned at spacings of 1 μm - 5 μm.

As will be clear from the foregoing description, the present
invention provides a high-performance rod lens array that can
be produced by the mechanically referenced method and which still
15   features good axial alignment without suffering the inconsistency
in the pitch on which gradient index rod lenses are arranged
and two types of inclination, height and horizontal.

Figs. 5A and 5B show an exemplary side plate that can be
used in the invention. To prepare a side plate 120, the entire
20   surface of the side of a side plate substrate 122 where lens
preformers 101 are to be placed is screen printed with a coating
to form an undercoat 126 which, in turn, is screen printed with
the same coating to form a striped pattern of ridges 128 that
extend along the lens preformers on the same pitch as the lens
25   pitch.

- 23 -

The side plate substrate 122 is an FRP plate and the coating is epoxy resin based. The undercoat 126 is formed by applying two layers of a coat to give a thickness (t_1) of 25 μm; the ridges have a thickness (t_2) of 25 μm that is relatively easy to control

5   in precision. The pitch of the ridges is set at a value near the maximum variation in the diameter of lens preformers that is anticipated in the manufacturing process.

An FRP plate has tiny asperities on the surface that have been caused by the texture of the woven glass fabric. The undercoat

10   is effective in reducing such tiny surface asperities. Using an epoxy resin based coating to form the undercoat and ridges is preferred since adequate bonding strength is insured at the interface with the resin to be impregnated between lens preformers.

Figs. 6A - 6C show steps in an example of the process of

15   the present invention for producing a rod lens array. In the invention, a grooved platen is used to array gradient index rod lens preformers. As shown in Fig. 6A, the grooved platen 102 is a member that has a multiple of shallow grooves 103 formed parallel to each other in the top surface of a flat metal plate

20   at equal spacings so that lens preformers 101 rest partially within the grooves; the platen 102 is a rectangle that is several hundred millimeters on each side. Each of the shallow grooves 103 has a V-shaped cross section and is sufficiently shallow that at least the upper half of a lens preformer 101 will stick

out when it is put in the groove. The difference between lens diameter D and the pitch of shallow grooves 103 is preferably set to be lie within the stated range of 1 μm – 5 μm. The lens preformers 101 are thin glass rods having a diameter of about

5   0.6 mm and a length of about 400 mm. The grooved platen 102 is supplied with a multiple of lens preformers 101 so that they are placed within the individual shallow grooves 103 and subjected to the following step of precision arrangement such that they make substantial contact with each other.

10   As shown in Fig. 6B, the grooved platen 102 rests on a work bench 134 with a heat insulating sheet 136 placed between the two parts. In a separate step, a thin impregnating resin sheet 138 is provisionally bonded to the side of the side plate 120 where the ridges have been formed. As in the prior art, the

15   resin sheet 138 may be a black resin sheet and to make this resin sheet, a resin having islands of a thermo-plastic resin dispersed in the matrix of a thermosetting resin is mixed with a black pigment (carbon black) and processed to a sheet in a thickness of about 80 μm. On top of the arrayed lens preformers 101, the

20   side plate 120 is placed to which the resin sheet 138 has been provisionally bonded. The resin sheet 138 is then heated to become viscous and given pressure under a weight 140 placed on top of the side plate 120. As a result, the resin in the resin sheet 138 flows into the gaps between the lens preformers 101

- 25 -

which are partially buried in the fluid resin. Any warpage of the lens preformers is straightened out since they are pressed onto the bottoms of the shallow grooves 103 while at the same time they are pressed onto the areas between ridges on the side

5   plate. Hence, if the resin is provisionally cured as such, the lens preformers 101 are fixed provisionally in a precision arranged state. Thereafter, the lens preformers 101 are detached from the grooved platen 102 to give a lens preformer array 142 which has the individual lens preformers buried partially in the resin

10   as shown in Fig. 6C. Reference numeral 139 represents the fluidized impregnating resin. Since the movement of each lens preformer 101 is constrained between adjacent ridges 128 on the side plate 120, the precision arrangement of the lens preformers 101 is maintained even if they are detached from the grooved platen

15   102.

To produce a single-row rod lens array, the step shown in Fig. 7 is added. On the side of the partially buried lens preformer array 142 where the lens preformers were placed in the previous step, another side plate 120 having the same striped pattern

20   of ridges as described above and a thin impregnating resin sheet 138 provisionally bonded by thermocompression to the side of the side plate 120 where the ridges have been formed are placed, with care being taken to position the second side plate such that each lens preformer is located between ridges. The resin

25   sheet 138 is then heated to become viscous and given pressure

- 26 -

under a weight 140. As a result, the impregnating resin in the resin sheet 138 flows to get into the gaps between lens preformers so that they are completely buried in the resin. The resin is then cured completely to fix the lens preformers. In this step, the movement of each lens preformer is constrained between ridges on the side plate, so there will be no departure from the desired precision arrangement of lens preformers.

Fig. 8 shows the single-row array of lens preformers that has been fabricated by the above-described procedure and which is generally indicated by 144, as sandwiched between two side plates 120. As in the prior art, the array 144 has such a structure that not only the gaps between lens preformers but also the gaps between each lens preformer and side plates have been thoroughly filled with the completely cured impregnating resin 139. The completely buried lens preformer array may optionally be cut off on both lateral sides; it is also cut by a specified length (lens length) in a direction normal to the longitudinal axes of the individual lens preformers, thereby yielding a gradient index rod lens array.

In the foregoing example, the impregnating resin sheet is given pressure by the simplest method of placing a weight. If desired, a hot press may be substituted. In practical applications, however, roll pressing is desirably adopted so that gradual pressure application proceeds from one end to the other as accompanied by displacement of air. Pressure application to

- 27 -

a plane sometimes fails to achieve complete removal of gas. In the present invention, the ridges formed on the side plate constrain the movement of lens preformers and this is particularly effective in preventing the departure from precise lens arrangement

5   even if the rolling pressing method is employed.

In the foregoing example, both side plates have a multiple of ridges. This is the most preferred for the purpose of minimizing the departure from precise lens arrangement. If desired, the side plate to be used with the lens preformers that are to be

10   buried partially in the impregnating resin may be provided with a striped pattern of ridges but the other side plate remains flat as in the prior art. With this design, the movement of lens preformers can be suppressed to some extent during thermal fusion, thereby reducing the departure from precise lens

15   arrangement.

To produce a two-row rod lens array, the step shown in Fig. 9 is added. Two partially buried lens preformer arrays 142 are prepared by the same procedure as in the foregoing example and placed in such a way that the sides where the lens preformers

20   101 are provided face each other, with another impregnating resin sheet 138 interposed. The resin sheet 138 is then heated to become viscous and given pressure under a weight 140. As a result, the resin flows into the gaps between lens preformers so that they are completely buried in the resin.

25   All resins including the one that has been cured provisionally

- 28 -

are then cured completely to fix the lens preformers. Fig. 10
shows the two-row array of lens preformrs that has been fabricated
by the above-described process and which is generally indicated
by 146, as sandwiched between two side plates 120. As in the
5   foregoing example, the array is then cut by a specified length
(lens length) in a direction normal to the longitudinal axes
of the individual lens preformers, thereby yielding a gradient
index rod lens array.

The resin sheet 138 to be used in the present invention
10   must be such that compared to the diameter of lens preformers
101 and their alignment pitch, it has an appropriate thickness
to fill the gaps between lens preformers. In the foregoing examples,
the resin sheet 138 is provisionally bonded to the side plate
before it is heated under pressure. Alternatively, the resin
15   sheet may simply be placed on the side plate and heated under
pressure.

In the foregoing examples, the striped pattern of ridges
is provided by screen printing but they may be provided by
photolithography. The ridges formed by photolithography have
20   more precise shapes than those formed by screen printing.

A photolithographic process of forming ridges is outlined
below.
(1) Apply a resist to the entire surface of one side of a side
plate.
25   For effective thickness control, a blanket resist coat is

- 29 -

desirably formed by applying an aqueous resist onto the side
plate through spray nozzles. In spray coating, the coating
thickness per application is set and a plurality of applications
are performed until the desired coating thickness is obtained.

5   .For example, an initial resist coat is applied in a thickness
of about 15 μm to planarize the side plate substrate by covering
its surface roughness; a subsequent resist coat is sprayed in
a thickness of 30 μm to control the resist thickness within a
range of 45 ± 5 μm. Resist materials are available in two types,

10   negative and positive. The negative-acting resist is such that
the part exposed to light is photopolymerized to become insoluble
in a liquid developer; in the case of the positive resist, the
exposed part becomes soluble. The positive resist has high image
resolution and the negative resist has somewhat lower image

15   resolution but it features good bonding property and high chemical
resistance. A suitable type of resist should be chosen depending
on use and other factors. In the example that follows, a
positive-acting resist having high image resolution was used.

(2) Paste a mask sheet.

20   A mask sheet from which a striped pattern of predetermined
shape has been cut out is pasted to the resist-coated surface
of the side plate.

(3) Exposure

            The unmasked areas of the resist layer are exposed to uv

rays to become soluble in a liquid developer.

(4) Etching

The mask sheet is stripped before etching (development).
Three major etching processes can be used: dip etching; paddle
5 etching; spray etching. Spray etching is preferred since it
has many advantages such as high etching rate, good etching
uniformity, and small undercuts.

(5) Cleaning

The developed surface is cleaned in the final step.
10 The above-described procedure gives a side plate having
a striped pattern of multiple ridges formed on the surface of
the side of a side plate substrate where lens preformers are
to be arranged; the ridges extend in the longitudinal direction
of lens preformers and are spaced apart on the same pitch as
15 the lens preformers. Using this side plate, one can produce
a rod lens array by bonding together gradient index rod lenses
such that they are located between ridges on the side plate as
in the foregoing examples.

As described on the foregoing pages, the invention provides
20 a process for producing a rod lens array which, on account of
the use of a grooved platen, can prevent lens preformers from
being positionally offset while they are arrayed. What is more,
the use of side plates having a multiple of ridges formed with
high precision allows the movement of lens preformers to be
25 constrained during installation of the side plates, thereby

suppressing the variation in the arrangement of lens preformers. As a result, the rod lens array produced can suitably be used as a component in an image writing system to insure higher precision in the imaging position.

5   In the process of the invention, ridges are formed on the side plate itself by screen printing or photolithography and, hence, a means for constraining the movement of lens preformers can easily be formed in high dimensional precision and at low cost, making the process of the invention adapted to volume
10   production of rod lens arrays and allowing for the use of lens preformers of smaller diameter.

        In the embodiment shown in Fig. 12, a multiple of rod lenses 101 are arranged in a row between two frame plates 220 and the gaps between rod lenses are filled with a black resin 139.
15   Thereafter, both end faces of each rod lens are optically polished to give a specified lens length, whereby a rod lens array 244 is fabricated. The black resin 139 may be a black silicone resin or a black epoxy resin. Hence, the black resin 139 not only fills the gaps between rod lenses 101 but also combines integrally
20   with the rod lenses 101. Both sides of the rod lens array 244 which are lateral to the direction of its width are formed of the frame plates 220. The frame plates 220 have preferably the same structure as the already mentioned side plates 120 but they may be flat plates (i.e., the side plate substrate 122).
25   In   the   embodiment   under   consideration,   the

- 32 -

center-line-average roughness is used as an index for the surface roughness of the peripheral surface of each rod lens 101 (see Fig. 22). Surface roughness may be measured with a roughness meter of stylus type. In the case of a rod lens, the stylus

5 is traversed over a specified sampling length L in the axial direction (x-direction). If the roughness curve obtained by the measurement is written as $y = f(x)$, the center-line-average roughness Ra is defined by the following equation:

$$Ra = \frac{1}{L} \cdot \int_0^L |f(x)| \, dx$$

10 where the position of the center line $(y = 0)$ is so determined as to satisfy the following equation:

$$\int_0^L f(x) \, dx = 0$$

The center-line-average roughness can be defined and measured in all positions on the peripheral surface of the rod lens.

15 In practice, however, rod lenses having a lens length from several millimeters to about 20 mm do not have significant variations on their peripheral surfaces, so the value determined from the surface roughness data obtained for a particular lens by measurement over a sampling length comparable to the lens length

20 along a straight line that passes through any desired point on its peripheral surface and which is parallel to its axis may safely be taken as the representative value for the lens. If necessary, two such straight lines may be drawn in different positions and the center-line-average roughness values as

25 determined from the surface roughness data taken on the respective

straight lines are averaged to give the representative value. The sampling length L may be set to be shorter than the lens length.

In the embodiment under consideration, the representative

5   value for the center-line-average roughness of each rod lens 101 is within the range of 0.5 μm - 2.0 μm. Hence, the representative value for the center-line-average roughness of the whole rod lens array composed of a plurality of rod lenses is also within the range of 0.5 μm - 2.0 μm.

10   In the embodiment under consideration, the representative value for the center-line-average roughness is between 0.01 μm and 0.2 μm as expressed by standard deviation for the whole rod lens array. The standard deviation is desirably determined from the measurements for all lens elements that constitute the lens

15   array; however, if the number of constituent lenses is so great that an unduly long time is taken to perform the measurement, sampling may be effected at specified intervals.

In the embodiment under consideration, representative values for the diameters of the individual rod lenses that constitute

20   a rod lens array are between 0.01 μm and 2.5 μm as expressed by standard deviation for the whole lens array. In this case, too, lens diameter is measured at one or more sites for each lens and if measurement is done at a plurality of sites, the average of the measured values is taken as the representative

- 34 -

value.

The MTF (modulation transfer function) of the rod lens array fabricated by the process described above is measured by the following procedure. An image of a rectangular wave grating pattern as produced from the rod lens array 244 is received by an optical sensor such as a CCD image sensor and from the illumination level of the received light, the response function (MTF) of the rod lens array is calculated by the following equation:

$$MTF(w) = \{i(w)max - i(w)min\}/\{i(w)max + i(w)min\}$$
$$\times\ 100\ (\%) \qquad \ldots\ (1)$$

where $i(w)max$ and $i(w)min$ are a maximum and a minimum value, respectively, of the rectangular wave response at a spatial frequency w (lp/mm) or a spatial frequency w (dpi). The closer to 100% the MTF is, the more faithful the produced image is to the original image. The measurement uses the monochromatic light obtained by passing halogen light through an optical filter at a wavelength of 740 nm. The pinhole array in the test chart had a density of 600 dpi or 1200 dpi and every other dot was turned on and off in the range of measurement.

The MTF which is an index for the optical performance of the rod lens array 244 generally reflects the resolving powers of the constituent rod lenses 101. Higher MTF values mean that the individual rod lenses 101 that compose the rod lens array 244 have high resolving power and vice versa. The reason is as follows. If the resolving power is high, the minimum value

- 35 -

of the rectangular wave response, i(w)min, in eq. (1) is small
and the ratio of the numerator to the denominator in eq. (1)
which represents the MTF value increases accordingly. For example,
if the response waveform is so close to the original image that
5   i(w)min is sufficiently near zero, both the numerator and the
denominator are sufficiently near i(w)max and the MTF value
approaches 100%.

.(Example 1)

        We now describe the center-line-average roughness of the
10   peripheral surface of the rod lens 101 and its variation as they
relate to the MTF value.

        Fig. 13 shows an exemplary surface texture of the peripheral
surface of the rod lens used in Example 1. The record in Fig.
13 was obtained by putting the probe of a surface roughness meter
15   of stylus type in contact with the peripheral surface of the
rod lens and traversing it parallel to the lens axis. Comparing
Fig. 13 with Fig. 19, one can see that the peripheral surface
of the rod lens of Example 1 was suppressed in both the
center-line-average roughness and its variation.

20   Fig. 20 is a graph showing the MTF values of comparative
array A. The average value of the center-line-average roughness
of array A is 2.17 μm and its standard deviation is 0.26 μm.
The average value and standard deviation of the center-line-average
roughness of the array can be determined by the following procedure:
25. a certain number of rod lenses are randomly sampled from the

whole group of the lenses that compose the array; the representative value is measured for the center-line-average roughness of each of the sampled lenses; the thus measured representative values are averaged and their standard deviations are determined (the

5   same procedure was used in the following description). The representative value for the center-line-average roughness of each lens is determined from the surface texture as obtained by tracing any desired straight line on the peripheral surface of the lens that extends parallel to its longitudinal axis over

10   a distance substantially equal to the entire lens length. Fig. 20 shows the MTF values as a function of the position in the longitudinal direction of the array.

Fig. 14 is a graph showing the MTF values of array B in Example 1. The average value of the center-line-average roughness

15   of array B for its peripheral surface was 1.70 μm and its standard deviation was 0.21 μm. Comparing with the data in Fig. 20, one can see that array B experienced smaller variations in MTF value with the position in the longitudinal direction.

Fig. 15 is a graph showing the MTF values of array C in

20   Example 1. The average value of the center-line-average roughness of array C for its peripheral surface was 1.39 μm and its standard deviation was 0.13 μm. Comparing with the data in Fig. 20, one can see that the MTF value of array C was substantially constant at varying positions in the longitudinal direction and hence

- 37 -

it was practically position-independent.

In order to describe the position-dependent variation of the MTF value, we introduce the parameter G, or an index for the variation in resolving power, which is calculated by the
5   following equation (2) as the ratio between MTFσ (the standard deviation of the MTF value for the whole array) and MTFave (the average value of MTF):

$G = (MTFσ/MTFave) \times 100$ (%) .   ... (2)

On the basis of the results of MTF measurement on arrays
10 A - C, the present inventors prepared. Table 1 which shows the relationships between the resolving power variation index G and each of the average value and deviation of the center-line-average (CLA) roughness of the peripheral surface of the constituent rod lens.

15 Table 3

Array	Average of CLA roughness of peripheral lens surface	Standard deviation of CLA roughness of peripheral lens surface	Resolving power variation index G
A	2.17 μm	0.26 μm	16.84
B	1.70 μm	0.21 μm	12.57
C	1.39 μm	0.13 μm	9.65

- 38 -

The result with array B shows that reducing the average
of the center-line-average roughness of the peripheral surface
of a rod lens to 2.0 μm and below was effective in suppressing
the variation in resolving power. However, if the average of

5   the center-line-average roughness of the peripheral lens surface
is unduly small, the effect of stray light becomes significant;
therefore, the average of the center-line-average roughness of
the peripheral lens surface is desirably at least 0.5 μm. Therefore,
the average of the center-line-average roughness of the peripheral

10   surface of a rod lens is desirably in the range of 0.5 μm - 2.0
μm. This means that the peripheral surfaces of individual rod
lenses should desirably have a center-line-average roughness
in the range of 0.5 μm - 2.0 μm.

In array C, the standard deviation of the center-line-average

15   roughness of the peripheral lens surface was further reduced
to less than 0.2 μm and this was effective in further suppressing
the variation in resolving power. Therefore, the standard
deviation of the center-line-average roughness of the peripheral
surface of a rod lens is desirably no more than 0.2 μm.

20   (Example 2)

The relationship between the MTF value and the variation
in the diameter of a rod lens is described in this example.

Fig. 21 shows the result of MTF measurement on comparative

- 39 -

array D. The data in Fig. 21 describes MTF values as a function of the position in the longitudinal direction of the array. The standard deviation of the diameter of each rod lens in the array D was 3.50 μm.

5   Fig. 16 shows the result of MTF measurement on array E of Example 2. The standard deviation of the diameter of each rod lens in the array E was 2.02 μm. Comparison with the data in Fig. 21 shows that the MTF value of array E was substantially constant at varying positions in the longitudinal direction and

10   hence it was practically position-independent.

On the basis of the results of MTF measurement on arrays D and E, the present inventors prepared Table 2 which shows the relationships between the resolving power variation index G and the variation in the diameter of the constituent rod lens.

15

Table 2

Array	Standard deviation of rod lens diameter	G
D	3.50 μm	8.15
20 E	2.02 μm	4.80

Obviously, the resolving power variation index G could be reduced by suppressing the variation in the diameter of the rod lens. The result with array E shows that the variation in the diameter of the rod lens is desirably held no greater than 2.5

- 40 -

μm.

  According to the foregoing embodiments of the present invention, the following advantages are achieved.

  (1) The average value of the center-line-average roughness of the peripheral surface of a rod lens is specified to lie within the range of 0.5 μm - 2.0 μm and this contributes to suppressing the variation that occurs in the resolving power of a rod lens array in the longitudinal direction.

  (2) The standard deviation of the center-line-average roughness of the peripheral surface of a rod lens is specified to lie within the range of 0.01 μm - 0.2 μm; as a result, variations are less likely to occur in the effective lens aperture which contributes to satisfactory image formation and the variation that occurs in the resolving power of a rod lens array in the longitudinal direction can be effectively suppressed.

  (3) The standard deviation of the diameter of a rod lens is specified to lie within the range of 0.01 μm - 2.5 μm; as a result, there is little chance for the occurrence of a departure from the desired lens array that would otherwise result from the variation in the diameter of the rod lens and the individual rod lenses in the rod lens array can be effectively protected against large inclinations from their optical axes.

  (4) By combining the features described in (1) and (2), the variation that may occur in the resolving power of a rod lens array in

- 41 -

the longitudinal direction can be suppressed in a more effective way. By combining the features described in (1) and (3) or those described in (1) - (3), the variation that may occur in the resolving power of a rod lens array in the longitudinal direction and the

5   off-axis inclinations of the individual rod lenses in the rod lens array can be effectively suppressed.

(5) The rod lenses are surrounded with a resin, so if the resin is a black resin that is a good absorber of light, any stray light that occurs in the rod lenses can be effectively absorbed.

10   (6) The use of frame plates offers the advantage that the rod lenses can be easily assembled into an array by using the frame plates as a guide in fabrication.

As described above, according to the present invention, rod lenses can be arranged with a small enough departure from

15   the desired alignment to produce a rod lens array that will experience minimum variations in resolving power in a longitudinal direction.

- 42 -